

PRODUCT INFORMATION



**\*Specifications**

|                      |       |                   |
|----------------------|-------|-------------------|
| Appearance           | ..... | White powder      |
| Saponification Value | ..... | 175 - 185 mgKOH/g |
| Acid Value           | ..... | Max. 3.0mgKOH/g   |
| Melting Point        | ..... | 80-90°C           |
| 200 mesh pass        | ..... | Min. 90.0%        |

**\*Uses**

- Lubricant for thermoplastic resin
- Mold releasing agent for rubber
- Lubricant for foaming agent
- Lubricant for engineering plastic(Dispersant for PC resin)

**\*Characteristics**

- Transparent

**\*Packaging**

20kg paper bag

**DAINICHI CHEMICAL INDUSTRY Co., Ltd.**

7-3-4, Nakaishikiri-cho, Higashiosaka-shi, Osaka-fu, 579-8014, Japan

TEL:072-985-1851 (60601)