

## PRODUCT INFORMATION

# DAIWAX BA-300

— N,N'-Ethylene-bis(stearamide) —

### \* Specifications

Appearance	. . . . .	White powder
Moisture	. . . . .	Max. 1.0%
Melting Point	. . . . .	140-150°C
Ash Content	. . . . .	Max. 0.1%
Acid Value	. . . . .	Max. 10.0mgKOH/g
Amine Value	. . . . .	Max. 10.0mgKOH/g
100 mesh on	. . . . .	Trace
145 mesh pass	. . . . .	Min. 95.0%
200 mesh pass	. . . . .	Min. 98.0%

### \* Uses

- Smoothing agent and anti-blocking agent for vinyl chloride, rigid ABS resin, and polystyrene resin
- Lubricant for casting (shell mold)
- Lubricant for wire drawing
- Surface gloss improver for rubber
- Binder for powder metallurgy
- Die lubricant

### \* Packaging

15kg paper bag

**DAINICHI CHEMICAL INDUSTRY Co., Ltd.**

7-3-4, Nakaishikiri-cho, Higashiosaka-shi, Osaka-fu, 579-8014, Japan

TEL:072-985-1851 (60601)